

# SYNTELAN 131

Lepilo za industriju nameštaja i  
građevinarstvo



**Syntelan 131** je jednokomponentno lepilo na bazi sintetičkog kaučuka rastvorenog u organskim rastvaračima. Otporno je na vodu i ulje.

## Tehničke karakteristike

Boja:	Svetlo braon
Viskozitet: (FØ6)	170-190 s
Gustina:	0,9g/cm <sup>3</sup>
Suva masa:	≥ 23%
Potrošnja:	≈ 200g/m <sup>2</sup>
Rok upotrebe:	12 meseci

## Namena

Lepilo **Sintelan 131** se koristi se u industriji nameštaja i građevinarstvu za lepljenje podnih pokrivača kao što su: guma, pluta, prostirači na bazi juta-filca i drugih sličnih materijala na beton, gips, drvo i drugo.

## Uputstvo za upotrebu

Pre upotrebe lepilo dobro promešati. Površine koje se lepe ohrapaviti i očistiti.

Pripremljene površine premazati (jednu i drugu stranu) lepilom (kožu i porozne materijale dva puta). Sušenje traje 10-15 minuta nakon čega se površine slepljuju i pritiskanjem presuju. Vezivanje traje 24časa.

## Napomena

Uputstvo o načinu upotrebe prilagoditi lokalnim uslovima rada i materijalima koji se lepe.

## Način isporuke

Lepilo se isporučuje u ambalaži od 1, 4 i 20 litara.

## Skladištenje

U dobro zatvorenim posudama na temperaturi od +5°C do +25°C (278K do 298K).



A. D. ELAN HEMIJSKA INDUSTRIJA, Ljubiše Miodragovića 11, 31300 Prijepolje, Srbija  
tel: 00381 (033) 781 350; fax: 00381 (033) 780 005; e-mail:[elanprodaja@ptt.rs](mailto:elanprodaja@ptt.rs); [www.elan.rs](http://www.elan.rs)

# SYNTELAN 131

Adhesive for furniture and construction  
industry



**Syntelan 131** is one component adhesive based on synthetic rubber solved in organic solvents. It is water and oil resistant.

## Technical characteristics

Colour:	Light brown
Viscosity (FØ6)	170-190 s
Density:	0,9g/cm <sup>3</sup>
Dry matter (%)	≥ 23%
Consumption:	≈ 200g/m <sup>2</sup>
Shelf life:	12 months

## Application

Adhesive **Syntelan 131** is used furniture and construction industry for bonding floor coverings like rubber, cork, coverings on the base of jute- felt and other materials to concrete, plaster, etc.

## Instruction for use

Mix the adhesive well before using. Surfaces must be roughened and cleaned. Apply the adhesive on previously prepared surfaces (both sides). Leather and other porous materials must be covered twice. Drying time is 10-15 minutes, after that bond the surfaces and press. Bonding lasts for 24 hours.

## Note

Instruction for use should be adjusted to local working conditions and materials that are used.

## Packing

Adhesive is available in packaging of 1; 4 and 20 liters.

## Storage

Keep in well sealed packaging at the temperature between +5°C to +25°C (278K do 298K).



A. D. ELAN HEMIJSKA INDUSTRija, Ljubiše Miodragovića 11, 31300 Prijepolje, Srbija  
tel: 00381 (033) 781 350; fax: 00381 (033) 780 005; e-mail:[elanprodaja@ptt.rs](mailto:elanprodaja@ptt.rs); [www.elan.rs](http://www.elan.rs)